

SELECT +

COLOUR LASER COPIER / PRINTERS

TPL 600

Transfer to Mugs, Tiles, Painted Metals, and Magnetic Material.

Handling : Leave in the plastic bag for storage to avoid excess humidity. Fan paper before use.

Application :

Print mirror image onto the coated (glossy) side. Make sure surface is free of figure prints(oil). Apply to all surface using a Thermal Pad (available from Trans Tech) between the heat press heat element and the transfer to bridge irregularities in the surface, as well as to spread heat evenly.

1. For Magnetic Material, 165°C for 70 sec with medium pressure. Cool peel.
2. For Printed Metal 185°C for 60 sec with medium pressure. Cool peel.
3. For Ceramics use 147°C for 70-90 seconds with HEAVY pressure. Cool peel.

Ceramics must be cured at 147°C for 10 minutes in an oven or toaster oven after transfer is applied to be microwave and dishwasher safe.

*If the toner does not release totally, use a higher temperature and or longer dwell time. Please conduct your own test to determine proper time and temperature for your specific application.



ASIA WINNER SDN BHD

NO 7, JALAN BUDI TENGAH 1, TAMAN WAWASAN PERINDUSTRIAN, 83000 BATU PAHAT, JOHOR, MALAYSIA.

Hunting Line : 607-428 9888 (5 LINES)

Fax : 607-428 9222

Email : info@asiawinner.com.my

Website: www.asiawinner.com.my