

SUPER JET

Cool Peel

SPJ-100

Super Jet heat transfer paper provides excellent printing quality for Roland SP300V & Mimaki JV3.

Heat Setting

Print temperature: 40-45 °C Degrees

Dryer temperature: 40-45 °C Degrees

Allow to dry for 2-3 minutes after printing.

Cut Pressure

Set to 50-60 grams

Cut Speed

Set to 15 cm/sec

Applications

1. Weed out the unprinted leaving the printed images on the backing sheet.
2. Apply **hot fix tape** (application sheet) over the top of the printed images & squeegee it firmly.
3. Remove printed images with the **hot fix tape**.

Transfer Process

1. Pre heat the fabric material for 5 sec to remove moisture.
2. Place the printed images with **hot fix tape** and position it to the desired location.
3. Heat press instructions as following :
 - a. Temperature 130-135 °C
 - b. Pressure 35-40 PSI
 - c. Time: 15-18 Sec.
 - d. Place **Teflon sheet** face down on it and press for 3-5 sec again.
 - e. Cool peel after 1-2 minutes.

ASIA WINNER SDN BHD

NO 7, JALAN BUDI TENGAH 1, TAMAN WAWASAN PERINDUSTRIAN, 83000 BATU PAHAT, JOHOR, MALAYSIA.

Hunting Line : 607-428 9888 (5 LINES)

Fax : 607-428 9222

Email : info@asiawinner.com.my

Website: www.asiawinner.com.my